

Quality	X39Cr13
According to Standard	EN 10088-3:2005 (E)
Number	1.4031



Comparable Standards

EN	W.N.	AISI
X39Cr13	1.4031	Type 420

Chemical Analysis

C % max	Mn %	Si % max	P% max	Cr %	Ni %	Mo %
0,36 to 0,42	≤ 1,00	1,00	0,040	12,5 to 14,5	—	—
S%	Others					
≤ 0,030 ^b	—					

Hot Work and Heat Treatment Tempera

Heat Treatment Symbol	Hot Forming		Annealing		Quenching		Tempering
	Temperature °C	Type of cooling	Temperature °C	Type of cooling	Temperature °C	Type of cooling	Temperature °C
+A	1100 to 800	slow cooling	750 to 850	furn., air	—	—	—
+QT 800	1100 to 800	slow cooling	—	—	950 to 1050	oil, air	650 to 700

Mechanical Properties at Room Temperature

Heat Treatment Condi	Ø mm.	Hardness HB ^c max	Rp0,2 ^d min. N/mm2	Rm ^d N/mm2 max 800	A ^d min. %	KV min. J
+A	—	245	—	max 800	—	—
+QT 800	≤ 160	—	650	850 to 1000	10	12